

Technical data

KEBAFLEX / SG 30 A.01

TPE-S, Shore A30, natur

Polymer: TPE-S

ISO designation: TPS-SEBS-MD

Productgroup: TPE

Brief description of the product family:

Unter dem Handelsnamen KEBAFLEX / S vertreiben wir ein Sortiment an thermoplastischen Elastomer-Compounds auf Basis SEBS/PP. KEBAFLEX / S ist in verschiedenen Shore-Härten von unter A10 bis über D50 verfügbar und wird wegen der kostengünstigen Verarbeitung im Spritzgussverfahren gerne als Ersatz für Gummi eingesetzt. Es ist weich und flexibel, frei einfärbbar, zeigt ein gutes elastisches Verhalten bis 100°C und bietet eine angenehme Haptik. Es steht ein breites Sortiment an modifizierten Compounds zur Verfügung, z.B. haftungsmodifizierte Typen für 2K-Spritzguss, bedruckbare Typen, Varianten mit optimiertem Druckverformungsrest, usw.

Properties:

flexible, good haptics, semi-crystalline, weich

Typical areas of application:

Industries:

Physical properties

Density in kg/m ³ ISO 1183-1	1170.00
---	---------

Mechanical properties

Breaking stress in MPa ISO 527-1	1.8
Elongation at break in % ISO 527-1	560.0
Compression set at 23°C in %. ISO 815-1	21
Compression set at 70°C in %. ISO 815-1	42
Shore A hardness DIN ISO 7619-1	30
Compression set at 100°C in % ISO 815-1	70
Stress at 10% elongation in MPa DIN EN ISO 527-1	0.20
Stress at 50% elongation in MPa DIN EN ISO 527-1	0.40
Stress at 100% elongation in MPa DIN EN ISO 527-1	0.60
Stress at 300% elongation in MPa DIN EN ISO 527-1	1.20

Rheological properties

Shrinkage in flow direction in % ISO 294-4	3.00
--	------

Rheological properties

Shrinkage transverse to the flow direction in % ISO 294-4	0.50
---	------

Thermal properties

Fire behavior (0.4 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (0.8 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (1.6 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (3.2 mm wall thickness) IEC 60695-11-10	HB

Processing instructions:**Pre-drying Recommendation:**

May be required to remove surface moisture:

Dryer type: dry air dryer

Temperature: 80°C

Drying time: 2 - 4 h

Residual moisture: < 0.02

Temperature recommendation:

Melt temperature: 200 - 250°C

Tool temperature: 20 - 50 °C

General processing notes:

The relatively high viscosity requires high injection speeds and medium injection pressure. To avoid high internal stresses, and to improve the 2K adhesion, the holding pressure should be kept as low as possible, and the holding times of injection pressure and holding pressure should be as short as possible.

Very good venting of the cavity is a basic prerequisite for achieving a high injection speed and, as a result, good adhesion and good surface quality.

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 27.02.2024

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de