

Technical data

KEBATER PBT A9030 nature 0191

PBT+PET, 30% glass fiber reinforced, suitable for food contact (EU)

Polymer: PBT/PET

ISO designation: PBT/PET-GF20-FC

Productgroup: PBT

Brief description of the product family:

KEBATER is the trade name of our range of thermoplastic polyesters. KEBATER products are characterized by good stiffness and strength, excellent electrical properties, advantageous fire properties and a good price-performance ratio. The product range includes PBT and PBT blends in different variants: unreinforced and glass fiber reinforced, impact modified, flame retardant, warp optimized as well as other compounds tailored to special requirements.

Properties:

dimensionally stable, good chemical resistance, good gliding properties, High strength, High stiffness, High wear resistance, semi-crystalline, approved for food contact (EU and FDA)

Typical areas of application:

Cover, Electronic components, Housing, Crockery and cutlery, Food packaging, Connecting elements

Industries:

Automotive, Electrical and electronics industry, Household appliances, Food processing industry, Mechanical Engineering, Sanitary industry

Physical properties

| | |
|--|---------|
| Water absorption in % in Anlehnung an ISO 62 | 0.15 |
| Density in kg/m ³ ISO 1183-1 | 1540.00 |

Mechanical properties

| | |
|---|-------|
| E-modulus in MPa ISO 527-1 | 10000 |
| Breaking stress in MPa ISO 527-1 | 140.0 |
| Elongation at break in % ISO 527-1 | 2.5 |
| Impact strength (Charpy) at 23°C in kJ/m ² ISO 179-1eU | 65.0 |
| Notched impact strength (Charpy) at 23°C in kJ/m ² ISO 179-1eA | 8.0 |

Rheological properties

| | |
|---|------|
| Shrinkage in flow direction in % ISO 294-4 | 0.20 |
| Shrinkage transverse to the flow direction in % ISO 294-4 | 0.90 |

Thermal properties

| | |
|--|-------|
| Melting temperature (DSC, 10°C/min) in °C ISO 11357-1/-3 | 225.0 |
|--|-------|

Thermal properties

| | |
|--|-------|
| Heat deflection temperature HDT (1.80 MPa) in °C ISO 75-1/-2 | 205.0 |
| Fire behavior (0.4 mm wall thickness) IEC 60695-11-10 | HB |
| Fire behavior (0.8 mm wall thickness) IEC 60695-11-10 | HB |
| Fire behavior (1.6 mm wall thickness) IEC 60695-11-10 | HB |
| Fire behavior (3.2 mm wall thickness) IEC 60695-11-10 | HB |

Electrical properties

| | |
|---|-------|
| Contact resistance in Ohm*m IEC 60093 | 1e+17 |
| Surface resistivity in ohms IEC 60093 | 1e+13 |

Processing instructions:**Pre-drying:**

Dryer type: dry air dryer.

Temperature: 100 – 120°C

Drying time: 2 – 4 h

Residual moisture: < 0.02%.

Temperatures:

Melt temperature: 255 – 275°C

Mold temperature: 80 – 120°C

Back pressure: max. 40 bar (specific)

Injection speed: medium to high

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 26.04.2024

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de