

Technical data KEBATER PBT BB130

PBT-GB30, PBT, 30% Glass balls

Polymer: PBT

ISO designation: PBT-GB30

Productgroup: PBT

Brief description of the product family:

KEBATER is the trade name of our range of thermoplastic polyesters. KEBATER products are characterized by good stiffness and strength, excellent electrical properties, advantageous fire properties and a good price-performance ratio. The product range includes PBT and PBT blends in different variants: unreinforced and glass fiber reinforced, impact modified, flame retardant, warp optimized as well as other compounds tailored to special requirements.

Properties:

dimensionally stable, Low warpage, good chemical resistance, Good electrical properties, good gliding properties, High strength, High stiffness, High wear resistance, semi-crystalline

Typical areas of application:

Electronic components, Housing, Plug, Structural components, Connecting elements

Industries:

Automotive, Electrical and electronics industry, Household appliances, Mechanical Engineering, Sanitary industry

Physical properties

Density in kg/m ³ ISO 1183-1	1510.00
---	---------

Mechanical properties

E-modulus in MPa ISO 527-1	4000
Breaking stress in MPa ISO 527-1	50.0
Elongation at break in % ISO 527-1	2.7
Impact strength (Charpy) at 23°C in kJ/m ² ISO 179-1eU	20.0
Notched impact strength (Charpy) at 23°C in kJ/m ² ISO 179-1eA	2.0

Rheological properties

Melt flow rate MFR (test condition)	250°C/2,16kg
Melt flow rate MFR in g/10min ISO 1133	25.0
Shrinkage in flow direction in % ISO 294-4	1.70
Shrinkage transverse to the flow direction in % ISO 294-4	1.70

Thermal properties

Melting temperature (DSC, 10°C/min) in °C ISO 11357-1/-3	225.0
--	-------

Thermal properties

Heat deflection temperature HDT (1.80 MPa) in °C ISO 75-1/-2	60.0
Heat deflection temperature HDT (0.45 MPa) in °C ISO 75-1/-2	155.0
Fire behavior (0.4 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (0.8 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (1.6 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (3.2 mm wall thickness) IEC 60695-11-10	HB

Electrical properties

Contact resistance in Ohm*m IEC 60093	1e+13
Surface resistivity in ohms IEC 60093	1e+13
Dielectric strength in kV/mm IEC 60243-1	19

Processing instructions:**Pre-drying:**

Dryer type: dry air dryer.

Temperature: 100 – 120°C

Drying time: 2 – 4 h

Residual moisture: < 0.02%.

Temperatures:

Melt temperature: 245 – 260°C

Mold temperature: 80 – 120°C

Back pressure: max. 40 bar (specific)

Injection speed: medium to high

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 27.04.2024

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de