

Technical data

KEBAFLEX - H / SPA1 70 A.03/1

TPE-S, Shore A68, modified for good adhesion to polyamides such as PA6, PA66, PA6.12 or partially aromatic PA grades such as GRIVORY GV or GRIVORY HT (manufacturer EMS-GRIVORY).

Polymer: TPE-S

ISO designation: TPE-S

Productgroup: TPE

Brief description of the product family:

Under the trade name KEBAFLEX / S we market a range of thermoplastic elastomer compounds based on SEBS/PP. KEBAFLEX / S is available in various Shore hardnesses from below A10 to above D50 and is often used as a substitute for rubber due to its cost-effective processing by injection molding. It is soft and flexible, freely colorable, shows good elastic behavior up to 100°C and offers a pleasant feel. A wide range of modified compounds is available, e.g. adhesion-modified grades for 2K injection molding, printable grades, grades with optimized compression set, etc.

Properties:

flexible, good haptics, adhesion modified, semi-crystalline, weich

Typical areas of application:

Sealing elements, Seals, Spring elements, Handles, Haptic components

Industries:

Automotive, Electrical and electronics industry, Household appliances, Industry, Mechanical Engineering, Furniture industry, Sports & Recreation

Physical properties

Density in kg/m ³ ISO 1183-1	1190.00
---	---------

Mechanical properties

Breaking stress in MPa ISO 527-1	6.0
Elongation at break in % ISO 527-1	420.0
Shore A hardness DIN ISO 7619-1	68
Stress at 10% elongation in MPa DIN EN ISO 527-1	0.80
Stress at 50% elongation in MPa DIN EN ISO 527-1	1.80
Stress at 100% elongation in MPa DIN EN ISO 527-1	2.20
Stress at 300% elongation in MPa DIN EN ISO 527-1	3.60

Rheological properties

Shrinkage in flow direction in % ISO 294-4	1.60
Shrinkage transverse to the flow direction in % ISO 294-4	0.30

Thermal properties

Fire behavior (0.4 mm wall thickness) IEC 60695-11-10	HB
---	----

Thermal properties	
Fire behavior (0.8 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (1.6 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (3.2 mm wall thickness) IEC 60695-11-10	HB

Processing instructions:**Pre-drying:**

Dryer type: dry air dryer

Temperature: 80°C

Drying time: 3 – 4 h

Residual moisture: < 0.02%.

Temperatures:

Melt temperature: 210 – 240°C

Tool temperature: 20 – 40 °C

General processing instructions:

Due to the pronounced structural viscosity of KEBAFLEX – H / SPA1 70 A.03/1, high injection speeds and short injection times should be aimed for. Fast injection improves adhesion to the hard component.

A compound temperature at the upper limit also improves adhesion.

Very good venting of the cavity is a basic prerequisite for achieving a high injection speed and, consequently, good adhesion and a good surface quality.

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 19.04.2024

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de