

Technical data KEBAFLEX / E 45.2

TPE-V, Shore A45

Polymer: TPE-V

ISO designation: TPE-V

Productgroup: TPE

Brief description of the product family:

Under the trade name KEBAFLEX / E we market a range of thermoplastic elastomer compounds based on EPDM/PP. KEBAFLEX / E is available in various Shore hardnesses from A35 to D50 and is often used as a substitute for rubber due to its cost-effective processing by injection molding. It is soft and flexible, freely colorable, shows good elastic behavior up to 120°C and offers a pleasant feel.

Properties:

flexible, good haptics, semi-crystalline, soft

Typical areas of application:

Seals, Bellows, Haptic components

Industries:

Automotive, Household appliances, Mechanical Engineering

Physical properties	
Density in kg/m ³ ISO 1183-1	950

Mechanical properties	
Breaking stress in MPa ISO 527-1	3.7
Elongation at break in % ISO 527-1	500.0
Shore A hardness DIN ISO 7619-1	45

Processing instructions:**Pre-drying recommendation:**

Dryer type: dry air dryer

Temperature: 70 – 75°C

Drying time: 2 – 4 h

Temperature recommendation:

Melt temperature: 190 – 210°C

Mold temperature: 20 – 40°C

Dwell time on the machine:

Aim for short dwell time, empty cylinder when production is interrupted, lower temperature, flush with fresh material when restarting.

General processing information:

The relatively high viscosity requires high injection speeds and medium injection pressure. To avoid high internal stresses, and to improve 2K adhesion, keep holding pressure as low as possible and select holding times of injection pressure and holding pressure as short as possible.

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 26.04.2024

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de