

Technical data

KEBAFLEX / P D25.1 gray 017001

Polyester-Elastomer, Shore D25

Polymer: TPC-ET

ISO designation: TPC-ET

Productgroup: TPE

Brief description of the product family:

KEBAFLEX / P stands for a range of thermoplastic polyester elastomers. This group of materials is characterized by very good flexibility and recovery behavior, constant properties over a wide temperature range, good sliding and wear behavior, and durability under dynamic loads.

Properties:

flexible, semi-crystalline, soft

Typical areas of application:

Cover, Sealing elements, Sliding elements, Haptic components, Food packaging, Toys

Industries:

Automotive, Household appliances, Industry, Agriculture, Food processing industry, Mechanical Engineering, Medical Technology, Sports & Recreation

Physical properties

Density in kg/m ³ ISO 1183-1	1010
---	------

Mechanical properties

Breaking stress in MPa ISO 527-1	7.5
Elongation at break in % ISO 527-1	650.0
Shore D hardness DIN ISO 7619-1	25
Stress at 10% elongation in MPa DIN EN ISO 527-1	1.30
Stress at 50% elongation in MPa DIN EN ISO 527-1	2.60
Stress at 100% elongation in MPa DIN EN ISO 527-1	3.40
Stress at 300% elongation in MPa DIN EN ISO 527-1	4.90

Rheological properties

Shrinkage in flow direction in % ISO 294-4	1.20
Shrinkage transverse to the flow direction in % ISO 294-4	1.30

Thermal properties

Fire behavior (0.4 mm wall thickness) IEC 60695-11-10	HB
---	----

Thermal properties

Fire behavior (0.8 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (1.6 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (3.2 mm wall thickness) IEC 60695-11-10	HB

Processing instructions:**Pre-drying recommendation:**

Dryer type: dry air dryer
Temperature: 60 – 80°C
Drying time: 2 – 4 h
Residual moisture: <0.04

Processing temperatures:

Mass temperature: 200 – 250°C
Tool temperature: 20 – 50 °C

General processing notes:

The relatively high viscosity requires high injection speeds and medium injection pressure. To avoid high internal stresses, and to improve 2K adhesion, the holding pressure should be kept as low as possible, and the holding times of injection pressure and holding pressure should be as short as possible.

Very good venting of the cavity is a basic prerequisite for achieving a high injection speed and, as a result, good adhesion and good surface quality.

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 16.04.2024

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de