

Technical data

KEBALLOY ECO FE 210205/7 R-PET (development product*)

KEBALLOY ECO FE 210205/7 R-PET is a 30% glass fibre reinforced PET compound. The PET base polymer is made from 100% post-consumer recycled PET bottles. KEBALLOY ECO FE 210205/7 R-PET is therefore a sustainable alternative to other glass fibre reinforced structural materials, e.g. as a metal substitute.

Polymer: PET

ISO designation: PET-GF30(REC)

Productgroup:

Brief description of the product family:

The name KEBALLOY ECO stands for a product range of engineering plastics and high-performance compounds based on post-consumer or post-industrial recyclate. KEBALLOY ECO compounds enable significant CO₂ savings compared to virgin materials and meet the highest requirements in terms of product properties and their uniformity from batch to batch. KEBALLOY ECO compounds also enable customer- or application-specific microcycles of engineering plastic parts and are thus a valuable contribution on the way to a circular plastics economy.

Properties:

dimensionally stable, good chemical resistance, good aging behavior, high continuous used temperature, High strength, High stiffness, semi-crystalline

Typical areas of application:

Fasteners, Hardware, Housing, Sliding elements, Bearing bushes, Structural components

Industries:

Automotive, Electrical and electronics industry, Industry, Agriculture, Mechanical Engineering, Furniture industry, Sports & Recreation

Physical properties

Density in kg/m ³ ISO 1183-1	1560
---	------

Mechanical properties

E-modulus in MPa ISO 527-1	10500
Breaking stress in MPa ISO 527-1	160.0
Elongation at break in % ISO 527-1	2.0
Impact strength (Charpy) at 23°C in kJ/m ² ISO 179-1eU	35.0
Notched impact strength (Charpy) at 23°C in kJ/m ² ISO 179-1eA	8.0

Thermal properties

Melting temperature (DSC, 10°C/min) in °C ISO 11357-1/-3	250.0
--	-------

Processing instructions:**Pre-drying:**

Dryer type: dry air dryer

Temperature: 80°C

Drying time: 4-8 h

Moisture content during processing: < 0.02%.

Recommended basic settings:

Melt temperature: 260 – 290°C

Mold temperature: 140 – 160 °C

Injection speed: high

Back pressure: 40 – 80bar (spec.)

Machine selection:

Screw: 3-zone screw with non-return valve

Nozzle: Open nozzle or shut-off nozzle

Wear protection: Wear protected according to machine manufacturer's recommendation, suitable for processing fiber reinforced plastics

Injection unit: Shot volume = 50-80% of the maximum metering volume

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 17.04.2024

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de