

Technical data

Privat: KEBABLEND / TC FE 210601/8 PA (development product*)

KEBABLEND / TC FE 210601/8 PA is a special compound based on PA6, which is thermally and electrically conductive.

Polymer: PA 6

ISO designation: PA6*-CF5-MD

Productgroup: THERMALLY CONDUCTIVE COMPOUNDS, Functionalized compounds

Brief description of the product family:

KEBABLEND is a wide range of functional compounds, often tailor-made to customer requirements. Under the trade name KEBABLEND, we market magnetizable, thermally or electrically conductive compounds, high-density injection molding materials, compounds for radiation protection applications, detectable plastics and much more.

Properties:

electrically conductive

Typical areas of application:

Pumps and motors, Pump housing, Structural components, Connecting elements

Industries:

Automotive, Household appliances, Industry, Mechanical Engineering, Furniture industry

Physical properties

Density in kg/m ³ ISO 1183-1	1610
---	------

Mechanical properties

E-modulus in MPa ISO 527-1	21700
Breaking stress in MPa ISO 527-1	95.0
Elongation at break in % ISO 527-1	0.6
Impact strength (Charpy) at 23°C in kJ/m ² ISO 179-1eU	9.2
Notched impact strength (Charpy) at 23°C in kJ/m ² ISO 179-1eA	2.4

Thermal properties

Melting temperature (DSC, 10°C/min) in °C ISO 11357-1/-3	220.0
Fire behavior (0.4 mm wall thickness) IEC 60695-11-10	HB
Thermal conductivity in plane in W/mK DIN EN 821	13.3
Thermal conductivity through plane in W/mK DIN EN 821	5.3
Fire behavior (0.8 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (1.6 mm wall thickness) IEC 60695-11-10	HB

Thermal properties

Fire behavior (3.2 mm wall thickness) IEC 60695-11-10	HB
---	----

Processing instructions:**Pre-drying:**

Dryer type: dry air dryer

Temperature: 80°C

Drying time: 4 – 8 h

Target moisture content: <0,1%

Recommended basic settings:

Melt temperature: 275 – 310

Mold temperature: 80 – 140

Injection speed: medium – high

Back pressure (spec.): 30 – 70 bar

Note higher thermal conductivity of the material when setting the barrel and mold temperature!

Machine selection:

Wear protection: Wear and corrosion protected as recommended by the machine manufacturer Suitable for processing highly filled compounds

Injection unit: Shot volume = 50-80% of maximum metering volume

Further important processing information:

The residence time of the melt in the screw antechamber should be kept as short as possible. If this is not observed, segregation can occur due to the large difference in density between the filler and the substrate if the downtimes are too high. The ideal here is metering time = cooling time. A medium back pressure leads to optimum homogenization. Due to the high filler content, the spraying equipment must be equipped with wear and corrosion protection.

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de