

Technical data

KEBALLOY ECO FE 221202 PBT/ASA (Development product*)

KEBALLOY ECO FE 221202 PBT/ASA is a 20% glass fiber reinforced PBT/ASA blend with 100% post-consumer recycled content.

Polymer: PBT/ASA

ISO designation: PBT/ASA-GF20

Productgroup: Recycling Compounds

Brief description of the product family:

The name KEBALLOY ECO stands for a product range of engineering plastics and high-performance compounds based on post-consumer or post-industrial recyclate. KEBALLOY ECO compounds enable significant CO2 savings compared to virgin materials and meet the highest requirements in terms of product properties and their uniformity from batch to batch. KEBALLOY ECO compounds also enable customer- or application-specific microcycles of engineering plastic parts and are thus a valuable contribution on the way to a circular plastics economy.

Properties:

dimensionally stable, good chemical resistance, good gliding properties, High strength, High stiffness, semi-crystalline

Typical areas of application:

Cover, Electronic components, Housing, Crockery and cutlery, Connecting elements

Industries:

Automotive, Electrical and electronics industry, Household appliances, Mechanical Engineering, Sanitary industry

Physical properties

Density in kg/m ³ ISO 1183-1	1450
---	------

Mechanical properties

E-modulus in MPa ISO 527-1	7000
Breaking stress in MPa ISO 527-1	115.0
Elongation at break in % ISO 527-1	3.0

Thermal properties

Fire behavior (0.4 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (0.8 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (1.6 mm wall thickness) IEC 60695-11-10	HB
Fire behavior (3.2 mm wall thickness) IEC 60695-11-10	HB

Processing instructions:

Pre-drying:

Dryer type: dry air dryer

Temperature: 120 – 140°C

Drying time: 2 – 4 h

Moisture content during processing: < 0.05%.

Recommended basic settings:

Melt temperature: 260 – 270°C

Mold temperature: 75 – 100 °C

Back pressure: 10 – 30 bar (spec.)

Injection speed: medium to high

Machine selection:

Screw: 3-zone screw with non-return valve

Nozzle: Open nozzle or shut-off nozzle

Wear protection: Wear protected according to machine manufacturer's recommendation, suitable for processing fiber reinforced plastics

Injection unit: Shot volume = 50-80% of the maximum metering volume

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 27.02.2024

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de